



# DERW GLASS LTD



## U-Value Chart - Double Glazing

All units manufactured to BS EN 1279, all glass toughened to BS EN 12150 C1 and laminated to BS EN 14449

Cavity gas	Clear		Pilks K			Pilks K "S"			Pilks Optitherm S1 +		
	Air	Argon	Air	Argon	Krypton	Air	Argon	Krypton	Air	Argon	Krypton
4/6/4	3.3	3.1	2.7	2.3	1.8	2.5	2.1	1.5	2.4	2.0	1.4
4/8/4	3.1	2.9	2.4	2.0	1.6	2.1	1.7	1.3	2.0	1.6	1.1
4/10/4	3.0	2.8	2.1	1.8	1.5	1.9	1.5	1.1	1.8	1.4	1.0
4/12/4	2.9	2.7	1.9	1.7	1.5	1.7	1.3	1.1	1.6	1.2	1.0
4/14/4	2.8	2.7	1.8	1.5	1.5	1.5	1.2	1.2	1.4	1.1	1.0
4/16/4	2.8	2.7	1.7	1.5	1.5	1.4	1.2	1.2	1.3	1.0	1.0
4/18/4	2.8	2.7	1.7	1.5	1.5	1.4	1.2	1.2	1.3	1.1	1.0
4/20/4	2.8	2.7	1.7	1.5	1.5	1.5	1.2	1.2	1.3	1.1	1.0





