



DERW GLASS LTD



U-Value Chart - Triple Glazing

All units manufactured to BS EN 1279, all glass toughened to BS EN 12150 C1 and laminated to BS EN 14449

Cavity gas	Clear		Pilks K			Pilks K "S"			Pilks Optitherm S1 +		
	Air	Argon	Air	Argon	Krypton	Air	Argon	Krypton	Air	Argon	Krypton
4/6/4/6/4	2.3	2.1	1.7	1.4	1.1	1.6	1.3	0.9	1.5	1.2	0.8
4/8/4/8/4	2.1	1.9	1.5	1.2	0.9	1.3	1.0	0.7	1.2	0.9	0.6
4/10/4/10/4	2.0	1.8	1.3	1.1	0.8	1.1	0.9	0.6	1.0	0.8	0.5
4/12/4/12/4	1.9	1.8	1.2	1.0	0.7	1.0	0.8	0.5	0.9	0.7	0.4
4/14/4/14/4	1.8	1.7	1.1	0.9	0.7	0.9	0.7	0.5	0.8	0.6	0.4
4/16/4/16/4	1.8	1.7	1.0	0.8	0.8	0.8	0.6	0.5	0.7	0.5	0.4
4/18/4/18/4	1.7	1.6	0.9	0.8	0.8	0.7	0.6	0.5	0.6	0.5	0.5
4/20/4/20/4	1.7	1.6	0.9	0.8	0.8	0.7	0.6	0.6	0.6	0.5	0.5

Where units contain a coated product 2 leaves will be coated and one clear/low iron